

TIMBERLINK[®] GREEN

DECKING

Treated Pine Decking



100% Renewable Plantation Pine

For use in outdoor, above ground applications (H3)

Lightweight for easy application

Can be easily painted or stained to fit your project colour scheme

TIMBERLINK[®]
Australia & New Zealand

TIMBERLINK[®] GREEN

Gap

For Dry Decking, i.e. LOSP, we recommend a 5mm gap between boards. For Wet Decking, i.e. Tan E, we recommend no gap between decking boards, to allow for shrinkage as the boards dry.

Which side up

Timberlink decking comes with a smooth side and a reeded side. It comes down to personal preference which side you would like facing up though reeded side down does reduce dirt build-up helping to prolong the life of the deck.

Fixings

Galvanised decking nails or decking screws should be used. In harsh environments stainless steel fixings may be required.

Finishes

It is strongly recommended that all timber decking is stained or painted with a suitable outdoor decking finish. If left unfinished timber exposed to the weather will fade to a silver grey colour and will develop splitting and surface checking.

Resealing

When cut, notched, drilled or rebated the exposed areas of treated timber should be resealed with a suitable resealing product to ensure a treatment envelope is maintained.

Treatment

All Timberlink decking is treated with a non-CCA chemical. Treatment chemical used can vary by state. All meet the relevant Australian Standards.

Sizes (mm)	90 x 22, 70 x 22 (also suitable for screening)
-------------------	--

Lengths (m)	1.8, 2.4, 3.0, 3.6, 4.2, 4.8, 5.4, 6.0
--------------------	--

Note: Not all sizes and lengths available all states.

